

SUTOP ÇİFT ELASTİK®**Cement and Acrylic Based Ready Elastic Waterproofing Mortar with Two Components****APPLICATION FIELD**

It is applied on wet surfaces such as terrace, bathroom, toilet and balcony, swimming pools, under basements, retaining walls as water isolation mortar.

APPLICATION**SURFACE PREPARATION**

The surface on which the application will be made should not have any pores or cracks. The surface should be free of substances such as oil, paint, dust. The particles on the surface should be removed (iron, wood etc.) and covered by the appropriate Entegre product. The application surfaces should be saturated with water prior to the application.

MORTAR PREPARING AND APPLICATION

Appropriate liquid (liquid component) quantity is placed in the mixing container (10 lt liquid component /25 kg powder). The whole bag is poured and mixed by hand mixer until all the lumps disappear. The mortar, after being rested for 5 minutes, is mixed until it is fluid again.

Fluid mortar is applied by a brush on the surface which can contact water. After the first coat dries, the second coat is applied as vertical to the first coat.

The surfaces for walking on are required to be covered by a final coat such as screed, ceramics etc.

The final coat should be applied after 1 day.

CONSUMPTION

1,5-2,0 kg / m² for single layer (uniform surface and suitable for single layer application under appropriate conditions. It may vary depending on surface properties and application conditions.)



1783

ENTEGRE HARÇ SAN. VE TİC. AŞ.

HÜSEYİNLİ KÖYÜ, BEYKOZ CAD. 222/4 ÇEKMEKÖY, İSTANBUL

15

1783 - CPR – 467

EN 1504-2

SUTOP ÇİFT ELASTİK

Two Components Water Insulation Mortar

Water Vapor Permeability	Class I
Capillary Water Absorption and Water Permeability	$\leq 0,1 \text{ kg/m}^2 \cdot \text{h}^{0,5}$
Adhesion Strength by pull-off	Flexible systems without trafficking
Reaction to fire	E Class
Hazardous Materials	No Contain



WARNING

Includes Portland Cement

Hazard Phrases

H315: Causes skin irritation

H317: May cause an allergic skin reaction

H318: Causes serious eye damage

H335: May cause respiratory irritation

Precautionary Phrases

P102: Keep out of reach of children

P280: Wear protective gloves/protective clothing/eye protection/face protection

P305+351+338+310: IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses if present and easy to do – continue rinsing. Immediately call a POISON CENTER/doctor

P302+P352+P333+P313: IF ON SKIN: Wash with plenty of water and soap. If skin irritation or a rash occurs: Get medical advice/attention

P261+304+340+312: IF INHALED: Avoid breathing dust/fumes/gas/mist/vapors/spray. Remove person to fresh air and keep comfortable for breathing. Get medical advice/attention if you feel unwell

P501: Dispose of contents/container.

STORAGE & PACKING

- It is offered in sets with 25 kg polyethylene reinforced kraft bags and 10 kg plastic drum.
- If desired, it can be dispatched on pallets.
- Under appropriate storage conditions, the shelf life is 1 year starting from the date of production. The component B freezes at the temperatures under 0 °C. It is recommended that the opened packages should be closed tightly, kept under appropriate storage conditions and should be consumed maximum within 1 week.

CERTIFICATE OF CONFORMITY



TS EN 1504-2 / April 2008

According to BS6920, it is suitable for contact with drinking water.

(METU-Chemical Engineering Department report no: 2016.03.04.09/02

Report date: 17.03.2016)

Above stated data obtained in lab conditions. Entegre will not be liable for any defect in product occurring by reason of events or conditions not within its control such as misuse, mishandling, improper storage or improper installation. Entegre reserves the right to revise the information contained herein without prior notice.

ENTEGRE HARÇ SANAYİ VE TİC. A.Ş.

Hüseyinli Mahallesi Beykoz Cad. No:222/4 34799 Çekmeköy/İSTANBUL T: 0216 434 50 96 F: 0216 434 50 31 www.entegreharc.com.tr