ŞAPSER® RAPID

Cement-Based, Ready-Mixed, Rapid-Setting Screed

FLOOR SOLUTIONS

Areas of Use

Used indoors and outdoors to obtain a smooth surface on floors where rapid results are required.

Advantages

- Ready to use.
- Saves time and labour.
- Ready for pedestrian traffic within 6 hours.
- Final floor covering can be applied within 24 hours.

Application

Surface Preparation

The application surface must be sound, clean and dry. The surface must be cleaned of paint, dust and any substances that may reduce adhesion.

Necessary repairs on existing floors must be carried out using suitable Entegre Repair Mortars.

Mortar Preparation and Application

Prepare the mortar by mixing with a hand mixer at a suitable speed for 2-3 minutes (3-3,5 L water / 25 kg bag).

Spread the mortar over the surface at a thickness of 3-10 cm, compact and level it with a screed. Since the prepared mortar begins to set within 10 minutes, prepare only as much mortar as can be applied within this period. Once the surface has hardened, smooth it using a mechanical trowel.

Consumption

18 kg/m^2 per 1 cm thickness.

Technical Values

Flexural Strength, N/mm^2	≥ 3
Compressive Strength, N/mm^2	≥ 7
Reaction to Fire Class	A1

Packaging and Storage

- Supplied on pallets in 25 kg bags.
- When stored unopened in its original packaging in a dry, frost-free environment, stacked no more than 8 bags high and without direct contact with the ground, the recommended shelf life is 1 year from the date of manufacture. Once opened, the bag should be used within 1 week.
- Keep the packaging tightly closed when the product is not in use.

Liability: Above stated data obtained in lab conditions. Entegre will not be liable for any defect in product occurring by reason of events or conditions not within its control such as misuse, mishandling, improper storage or improper installation. Entegre reserves the right to revise the information contained herein without prior notice.

Hüseyinli Mah. Beykoz Cad. No: 222/4 Çekmeköy - İstanbul
+90 (0216) 434 50 96
export@entegreharc.com.tr

Warnings

- Do not add any foreign material (lime, cement, gypsum, etc.) to the prepared mortar.
- Mortar that has exceeded its working time must not be mixed with water or dry mortar and reused.
- Application is recommended at temperatures between +5 °C and +35 °C.
- For applications over very large areas, provide expansion joints at suitable intervals (for areas larger than 25 m^2).
- Do not apply to frozen surfaces.
- Do not apply under direct sunlight.
- Do not use outside the specified areas of application or contrary to the application instructions.
- Do not inhale directly. In case of contact with eyes, rinse thoroughly with plenty of water and seek medical advice if necessary.
- Request the product Safety Data Sheet for further information.
- Please consult us regarding all other application conditions and technical questions.

Certificate of Conformity

TS EN 13813 / December 2004 / CT-C7-F3

Liability: Above stated data obtained in lab conditions. Entegre will not be liable for any defect in product occurring by reason of events or conditions not within its control such as misuse, mishandling, improper storage or improper installation. Entegre reserves the right to revise the information contained herein without prior notice.

ENTEGRE
Hüseyinli Mah. Beykoz Cad. No: 222/4 Çekmeköy - İstanbul
+90 (0216) 434 50 96
export@entegreharc.com.tr