

FINTEK®**Cement Based Thin Finishing Plaster****APPLICATION FIELD**

Applied on interior and exterior places, upon traditional plaster and ready mix plaster as a last cover .

CHARACTERISTICS

- It provides a smooth surface for the last cover.
- It gives cost advantage.
- It is easy and fast to apply

APPLICATION**SURFACE PREPARING**

- The surface must be absolutely purified from form oil, dust, paint and adherence reducing materials.
- All the holes must be filled and repairs must be made with the same material or appropriate Entegre Repair Mortars before application.
- Application surface must be dampened. with water if necessary

MORTAR PREPARING AND APPLICATION

- FİNTEK® mixed with an electrical drill or by hand (4,5-5 lt water / 25 kg bag)..
- Application thickness must be between 3-10 mm in one coat
- Surface is leveled.
- FİNTEK® is polished when the surface becomes hard enough and if necessary the operation is completed by a dampened sponge.

CONSUMPTION

For 1 cm plaster thickness, the consumption is approximately 1,7 kg/m².

TECHNICAL DATA

Dry Bulk Density of Hardener Mortar, kg/m ³	1600 ± 300
Compressive Strength, N/mm ²	≥6 (CS IV)
Adhesive Strength, N/mm ²	≥0,2 (FP:B)
Capillary Water Absorbtion, kg/m ² .min ^{0,5}	W0
Water Vapour Permeability, μ	≤ 25
Thermal Conductivity, W/m.K	≤ 0,93 (λ _{10,dry}) W/mK
Reaction to fire	A1

SPECIAL SUGGESTIONS

- No other materials (lime, cement, gypsum, etc.) must be added into the prepared mortar.
- Suggested that the application is done between +5°C, +35°C.
- FİNTEK® should be protected against quick drying in windy weather conditions.
- For the durability of plaster ,in 3 days after the application, depending on weather conditions the surface must be dampened at intervals.
- Speed drying make be cracks. For this reason,suggested double application.
- Fiber mesh must be used at the intersection of different materials and at points, where some movements can occur.
- For the application on FİNTEK®, according to the weather conditions, must be waited for at least 10 days.
- Do not go beyond the application field and rules.
- As it is cement based product, do not smell it directly. Wash your eyes in case of contact. Call your doctor if it is necessary.
- For detailed information please request security data sheet.
- Contact us for the other application fields and for your technical questions.

STORAGE & PACKING

- 25 kg kraft paper or polypropylene bags, in the sling or shrink covered pallets upon request.
- 1 year from the date of manufacture if stored in unopened original package; under dry, frost free conditions and arranged maximum 8 bags one above the other. Suggested to be consumed in 1 week after the package is opened.

CERTIFICATE OF CONFORMITY



TS EN 998-1: Ferbruary 2017 A1-GP-CS IV-W0

Above stated data obtained in lab conditions. Entegre will not be liable for any defect in product occurring by reason of events or conditions not within its control such as misuse, mishandling, improper storage or improper installation. Entegre reserves the right to revise the information contained herein without prior notice.

ENTEGRE HARÇ SANAYİ VE TİC. A.Ş.

Hüseyinli Köyü Beykoz Cad. No:222/4 34799 Çekmeköy/İSTANBUL T: 0216 434 50 96 F: 0216 434 50 31 www.entegreharc.com.tr