

ALÇIMATİK PLUS®

Concentrated Machine-Applied Plaster

APPLICATION FIELD

Applied on brick, concrete, autoclaved aerated concrete, fair faced concrete, bims, briquette, walls and ceilings in the interior faces of buildings.

APPLICATION

ALÇIMATİK PLUS®, is mixed (14 lt water / 25 kg bag) and sprayed on the surface with ready mix plaster mixing and spreading machine. Application thickness must be between 8 mm and 25 mm in the first coat. If the thickness is more than 25 mm, second coat is applied in max. 25 mm thickness. Surface is levelled. Approximately one hour later after the latest application, it is levelled again. When surface becomes hard that it can not be levelled, it is smoothed by steel spatula.

ALÇIMATİK PLUS® surface is dampened and trifled to have a satin surface. According to weather conditions, after 10-15 min, by applying steel trowel, perfect surface is obtained. After 2 hours when the surface becomes tough, it is dampened and finished by steel towel.

CONSUMPTION

For 1 cm plaster thickness, the consumption is approximately 8,0 kg/m².

	
ENTEGRE HARÇ SAN. VE TİC. AŞ. HÜSEYİNLİ KÖYÜ, BEYKOZ CAD. 222/4 ÇEKMEKÖY, İSTANBUL 19	
TS EN 13279-1 Lightweight Gypsum Building Plaster B4 / 50 / 2 ALÇIMATİK PLUS	
Reaction To Fire	A1
Setting Time, dk	> 50
Compressive Strength, N/mm ²	≥ 2,0
Flexural Strength, N/mm ²	≥ 1,0

PACKAGING AND STORING

- 25 PP bags, in the sling or plastic covered pallets upon request.
- 6 months from the date of manufacture if stored in unopened original package; under dry, frost free conditions and arranged maximum 8 bags one above the other layer. Recommended to be consumed in 1 week after the bag is opened.

SPECIAL SUGGESTIONS

- The surface must be purified from form oil, dust, paint and adherence reducing materials.
- Suggested that the application is done between +5°C, +35°C.
- Fiber mesh must be used at the intersection of different materials and at points, where some movements can occur.
- Don't go beyond the application field and rules.
- As it is gypsum based product, do not smell it directly. Wash your eyes in case of contact. Call your doctor if it is necessary.
- For detailed information please request security data sheet.
- Contact us for the other application fields and for your technical questions.

CERTIFICATE OF CONFORMITY



**It has been producing in accordance with
EN 13279-1 February 2009 / B4-50-2,0**

Above stated data obtained in lab conditions. Entegre will not be liable for any defect in product occurring by reason of events or conditions not within its control such as misuse, mishandling, improper storage or improper installation. Entegre reserves the right to revise the information contained herein without prior notice.

ENTEGRE HARÇ SANAYİ VE TİC. A.Ş.

Hüseyinli Köyü Beykoz Cad. No:222/4 34799 Çekmeköy/İSTANBUL T: 0216 434 50 96 F: 0216 434 50 31 www.entegreharc.com.tr