

RENDERCOAT® 2 MM

Natural, Decorative, White View On The Sides Of The Buildings

APPLICATION FIELD

Applied on exterior sides of buildings and heat insulation systems as a decorative coating plaster.

CHARACTERISTICS

High resistance to water and frost.

Natural and decorative view.

Easy to apply.

APPLICATION**SURFACE PREPERATION**

The surface must be purified from form oil, dust, paint and adherence reducing material. On the plastered surface must be taken measures against dust. Entegre repair mortars can be used for filling. Application field must be dampened with water and than application can start.

MORTAR PREPARATION & APPLICATION

Appropriate water quantity is put in a pot. (6,5-7 lt. water / 25 kg bag) powder is added and mixed with a hand mixer. Should be waited for 5 minutes and then mixed again to obtain a fully homogeneous product. Ready mortar is applied with equal thickness by a steel trowel to the surface. Application thickness must be 2 mm..

CONSUMPTION

2-3 kg/m²

TECHNICAL DATA

Brightness	No value required
Dry Film Thickness	> 400; E ₅
Particle Size Class μm	<1500; S ₄
Water Vapor Transferring Speed, g/m².d	V ₀
Water Transferring Speed, kg/m²,h^{0,5}	W ₀
Crack Briding Property Class	A ₀

CO ₂ Permeability Class						C ₀	
Mold Growth Resistance Class						K ₂	
TS EN 1062-1	E ₅	S ₄	V ₀	W ₀	A ₀	C ₀	K ₂

PACKAGING AND STORING

- 25 kg polyethylene reinforced kraft bags, in the sling or shrink covered pallets upon request.
- Shelf life is 1 year from the date of manufacture if it is stored in unopened original package; under dry, frost free conditions and arranged maximum 8 bags one above the other, suggested to be consumed in 1 week after the package is opened.
- Keep kraft bags mouth close when it not in use.

WARNINGS

- No other materials (lime, cement, gypsum etc..) should be added to the prepared mortar.
- Mortar should not be used again after date of expiry by mixing with water or dry mortar.
- TURUNCU PAKET® DEKORATİF KAPLAMA SIVASI application must be done at least 5 days after plaster application (may vary according to weather conditions.)
- To resistance of plaster,surface should be watered for 3 days with regular intervals and depend on the weather conditions.
- Suggested that the application is done between +5°C, +35°C.
- TURUNCU PAKET® DEKORATİF KAPLAMA SIVASI should be protected against quick drying in windy weather conditions.
- It should not be applied on the frozen surfaces.
- Don't apply under direct sunlight.
- Don't go beyond the application field and rules.
- Don't smell it directly. Wash your eyes in case of contact. Call your doctor if it is necessary.
- For detailed information please request security data sheet.
- Contact us for the other application fields and for your technical questions.

CERTIFICATE OF CONFORMITY



TS 7847 / E5-S4-V0-W0-A0-C0

Above mentioned data has been obtained in laboratory environment. Please get in touch with our Technical Department for more detail.

Entegre reserves right to amend the abovementioned information and data.

Entegre will not be held responsible from the failures due to improper use and applications.