

ENTEGRE

"Building Life"

PRIMEL 600® BETOKONTAKSynthetic Resin Dispersion-Based
Adhesion-Promoting PrimerCOMPLEMENTARY AND
AUXILIARY PRODUCTS

Fields of Application

Used as an adhesion primer on ceramic surfaces and exposed concrete walls and ceilings.

Properties

- Increases the bond strength of plaster.
- Helps prevent shrinkage cracks in plaster.
- Used for priming applications over ceramic surfaces.
- Prevents rapid water loss and extends plaster working time.
- Enables easy application.
- Saves labour.

Application

Surface Preparation

The surface must be dry, sound, clean and free of oil.

Mixture Preparation and Application

For use beneath plaster, dilute at a ratio of 1:3;

- 1,6 kg Water / 5 kg PRIMEL 600® BETOKONTAK
- 4 kg Water / 12 kg PRIMEL 600® BETOKONTAK

For applications over ceramic surfaces, dilute at a ratio of 1:5;

- 1 kg Water / 5 kg PRIMEL 600® BETOKONTAK
- 2,4 kg Water / 12 kg PRIMEL 600® BETOKONTAK

Dilute with water before use. The stated water quantities are maximum values; a thicker consistency may be used if required.

Mix PRIMEL 600® BETOKONTAK and water until homogeneous. Stir the diluted primer intermittently during application.

Apply PRIMEL 600® BETOKONTAK with a roller or brush. Apply plaster once the material cannot be scraped from the surface.

Consumption

200 g/m² (at a ratio of 1:3)

335 g/m² (at a ratio of 1:5)

Document No: TDS.ENG.07.06

Revision No: 1

Validity Date: 20.08.2026

Liability: Above stated data obtained in lab conditions. Entegre will not be liable for any defect in product occurring by reason of events or conditions not within its control such as misuse, mishandling, improper storage or improper installation. Entegre reserves the right to revise the information contained herein without prior notice.



Hüseyinli Mah. Beykoz Cad.
No: 222/4 Çekmeköy - İstanbul

+90 (0216) 434 50 96

export@entegreharc.com.tr

Page 1



Technical Values

Density, kg/L	~ 1,5
Colour	Pink
pH	7,0 – 9,0
Application Thickness, mm	Max. 3
Initial Bond Strength, N/mm ²	≥ 1,0
Drying Time, min (20 °C and 50% Relative Humidity)	60–120
Temperature Resistance, °C	-20 / +80

Packaging and Storage

- Packaged in 5 kg and 12 kg plastic buckets.
- Store in closed areas away from direct sunlight.
- Shelf life: 1 year from production date, unopened in original packaging, in a dry, frost-free environment.

Warnings

- Application is recommended at temperatures between +5 °C and +35 °C.
- Provided the container is kept closed, use within 3 days after dilution.
- The application surface must be dust-free, dry and clean.

- Protect from frost.
- Wash all tools with water after application.
- Harmful if swallowed.
- Keep out of reach of children.
- Keep the container tightly closed.
- Avoid contact with eyes and skin. Consult us for other application conditions and technical questions.

Certificate of Conformity



TS 13744 / March 2017

Class 1: Filled Adhesion-Promoting Primer