



Fields of Application

- For preparing a bonding spatter coat with PRİMEL® powder before plastering,
- For improving the adhesion and strength performance of plaster mortars,
- For bonding old and fresh concrete,
- For improving adhesion and surface performance when preparing screeds.

Properties

- Improves performance as a bonding admixture in screeds and plasters.
- Increases resistance to cracking and abrasion.
- Provides excellent adhesion and elasticity.

Application

When used as a bonding spatter coat before gypsum and cement-based plasters, dilute PRİMEL 200® with water at a ratio of 1:3 and mix with PRİMEL® powder.

Warnings

- Application is recommended at temperatures between +5 °C and +30 °C.

Apply to the surface as a spatter coat by hand or with a spray machine. Proceed with plastering after drying. For plaster and screed applications, use a PRİMEL 200®/water mixture prepared at a ratio of 1:24 as the mixing liquid.

Consumption

Approximately 150 g/m² for PRİMEL®

Approximately 100 g/m² for screed

Technical Values

Density, kg/L	≈1.08
Colour	White
pH	≈6
Drying Time (for Spatter Coat), Hours	≈1

Packaging and Storage

- Packaged in 10 and 30 litre plastic containers.
- Shelf life is 1 year from the date of manufacture when stored unopened in its original packaging in a dry environment protected from frost.
- The application surface must be dust-free, dry and clean.
- Protect from frost.

The logo for Entegre, featuring the word "ENTEGRE" in white capital letters on a green rectangular background with a stylized orange and white graphic element.

PRİMEL 200®

"Building Life"

Bonding Admixture Enhancing
Adhesion and Water Resistance



COMPLEMENTARY AND
AUXILIARY PRODUCTS

- Wash all tools with water after application.
- Harmful if swallowed.
- Keep out of reach of children.
- Keep the container tightly closed.
- Avoid contact with eyes and skin.
- Please consult us regarding any other application conditions and technical questions.

Document No: xxxxxxxxxxxxxxxxxxxxxx

Revision No: xxxxxxxxxxxxxxxxxxxxxx

Validity Date: xxxxxxxxxxxxxxxxxxxxxx

Liability: Above stated data obtained in lab conditions. Entegre will not be liable for any defect in product occurring by reason of events or conditions not within its control such as misuse, mishandling, improper storage or improper installation. Entegre reserves the right to revise the information contained herein without prior notice.



Hüseyinli Mah. Beykoz Cad. +90 (0216) 434 50 96
No: 222/4 Çekmeköy - İstanbul ✉ export@entegreharc.com.tr

Page 2