

ENTEGRE

FUGAFIX GENİŞ® SİLİKONLU

"Building Life" Cement-Based, Silicone-Modified, High-
Performance, Ready-Mixed Wide-Joint Grout
(5 Different Color Options for 6-15 mm Joint)



TILE ADHESIVES AND
GROUTING MORTARS

Areas of Use

Used indoors and outdoors, in wet areas and in horizontal and vertical applications, for filling 6-15 mm joints between stone, brick and Khorasan brick materials.

Advantages

- Easy to apply.
- Provides a smooth appearance.
- Can be used easily on horizontal and vertical surfaces indoors and outdoors.
- Highly water-repellent. Resistant to water and frost

Application

Surface Preparation

Before application, any dust, shavings, and construction or cement residues in the joints must be scraped off and cleaned with a brush.

The joints must be dampened with water before application.

Mortar Preparation and Application

- First, water is poured into the mixing container, and then FUGAFIX WIDE® SILICONE is added (5.0-5.5 L of water/25 kg bag) and mixed until the lumps disappear. A low-speed mixer is recommended. The mixture is left to stand for 5 minutes and then mixed again to obtain a homogeneous consistency.
- The prepared mortar is applied at a suitable thickness using a rubber-edged spatula.
- Approximately 30 minutes after application, the surface is cleaned with a damp sponge. This period may be shorter when the ambient temperature is high or when covering materials have a high water absorption rate.
- If wiping is performed too early or with an excessively wet sponge, waviness may occur on the joint surface. The sponge must be cleaned frequently.

Document No: TDS.ENG.04.14

Revision No: 1

Validity Date: 25.08.2026

Liability: The above data were obtained under laboratory conditions. Entegre shall not be held liable for any problems or damages arising from use of the product for purposes other than those specified, failure to comply with the stated storage, preservation and application conditions, or incorrect application. Entegre reserves the right to update and amend the above information without prior notice.



Hüseyinli Mah. Beykoz Cad.
No: 222/4 Çekmeköy - İstanbul

+90 (0216) 434 50 96

export@entegreharc.com.tr

- After ensuring that FUGAFIX WIDE® SILICONE has dried in the joint, any residue remaining on the surface must be cleaned with a dry cloth. If application is carried out in a very hot environment (above 28 °C), the application surface must be very lightly dampened after 1 day.
- If the surface has not been cleaned sufficiently, grout residue on the covering may be cleaned after 10 days with a suitable cement stain remover (PRİMEL 300®).

Consumption

	Joint Width (mm)		
Tile Size (cm)	5 mm (g/m ²)	10 mm (g/m ²)	15 mm (g/m ²)
10*20	1000	1730	2590
15*15	920	1530	2300
15*20	800	1340	2000
20*20	690	1150	1730
20*25	1000	1650	2490
20*30	920	1530	2300
33*33	670	1110	1680

Technical Values

Technical Values	Value
Pot Life, Hours	< 2
Water Absorption After 30 Min, g (TS EN 13888-2)	≤ 2
Water Absorption After 240 Min, g (TS E3888-2)	≤ 5
Shrinkage, mm/m (TS EN 13888-2)	≤ 3
Flexural Strength After Dry Storage, N/mm ² (TS EN 13888-2)	≥ 2,5
Flexural Strength After Freeze-Thaw Cycles, N/mm ² (TS EN 13888-2)	≥ 2,5
Compressive Strength After Dry Storage, N/mm ² (TS EN 13888-2)	≥ 15

ENTEGRE

FUGAFIX GENİŞ® SİLİKONLU

"Building Life" Cement-Based, Silicone-Modified, High-
Performance, Ready-Mixed Wide-Joint Grout
(5 Different Color Options for 6-15 mm Joint)



TILE ADHESIVES AND
GROUTING MORTARS

Compressive Strength After Freeze-Thaw Cycles, N/mm ² (TS EN 13888-2)	≥ 15
Abrasion Resistance, mm ³ (TS EN 13888-2)	≤ 1000

- Mortar whose pot life has expired must not be mixed with water or dry mortar and reused.
- After bonding, at least 24 hours must be allowed before grouting.
- Application at temperatures between +5 °C and +30 °C is recommended.
- Do not apply on frozen surfaces.
- After grouting, protect the joint surface from water drops, direct water application, splashing, and similar exposure until the joints have dried.
- A suitable cement cleaner (PRİMEL 300®) must be used to clean soiled joints.
- Do not use outside the specified application areas and instructions for use.
- Do not inhale directly. In case of contact with eyes, rinse with plenty of water and seek medical advice if necessary.
- After application, hands and application tools must be washed with plenty of water.

Packaging and Storage

- Supplied on pallets in 25 kg kraft bags.
- The shelf life is 1 year from the date of production when stored unopened in its original packaging in a dry, frost-free environment, stacked no more than 8 bags high and without direct contact with the floor; after opening the bag, consumption within 1 week is recommended.
- Keep packages tightly closed when not in use.

Warnings

- No foreign material (lime, cement, gypsum, etc.) must be added to the prepared mortar.

Document No: TDS.ENG.04.14

Revision No: 1

Validity Date: 25.08.2026

Liability: The above data were obtained under laboratory conditions. Entegre shall not be held liable for any problems or damages arising from use of the product for purposes other than those specified, failure to comply with the stated storage, preservation and application conditions, or incorrect application. Entegre reserves the right to update and amend the above information without prior notice.



Hüseyinli Mah. Beykoz Cad.
No: 222/4 Çekmeköy - İstanbul

+90 (0216) 434 50 96

export@entegreharc.com.tr

ENTEGRE

FUGAFIX GENİŞ® SİLİKONLU

"Building Life" Cement-Based, Silicone-Modified, High-
Performance, Ready-Mixed Wide-Joint Grout
(5 Different Color Options for 6-15 mm Joint)



TILE ADHESIVES AND
GROUTING MORTARS

- For further information, request the product safety data sheet.
- Please consult us regarding all other application conditions and for your technical questions.

Certificate of Conformity

**G**

TS EN 13888-1 / September 2022 / CG2WA

CG2WA: Improved cementitious grout with additional characteristics of reduced water absorption and high abrasion resistance

Ministry of Public Works Item No: 10.300.2231

Document No: TDS.ENG.04.14

Revision No: 1

Validity Date: 25.08.2026

Liability: The above data were obtained under laboratory conditions. Entegre shall not be held liable for any problems or damages arising from use of the product for purposes other than those specified, failure to comply with the stated storage, preservation and application conditions, or incorrect application. Entegre reserves the right to update and amend the above information without prior notice.



Hüseyinli Mah. Beykoz Cad.
No: 222/4 Çekmeköy - İstanbul

+90 (0216) 434 50 96

export@entegreharc.com.tr