

ENTEGRE

"Building Life"

SATENPER®Satin Finishing Plaster
Ready-to-Paint Surface

GYPSUM PLASTERS

Areas of Use

Used as a final coat on gypsum- or cement-based plasters and surfaces coated with fine plaster in interior spaces.

Properties

- Provides comfortable and easy application thanks to its long working time and putty-like consistency.
- Provides an excellent finish before painting.

Application

Surface Preparation

The surface must be thoroughly cleaned of formwork oil, dust, paint and substances that reduce adhesion.

Mortar Preparation and Application

After surface cleaning is completed, water is first added to the mixing container, then SATENPER® is added (17-18 L water/25 kg bag) and mixed until all lumps are eliminated. Allow to stand for 5 minutes, then mix again to obtain a homogeneous mixture. The prepared mortar is applied to the surface with a steel trowel at a thickness of 1-2 mm. Before painting, the surface is lightly sanded with fine sandpaper to complete the application.

Consumption

Approx. 1,0 kg/m² for 1 mm plaster thickness.

Technical Values

Compressive Strength, N/mm ²	≥ 2,0
Flexural Strength, N/mm ²	≥ 1,0
Adhesion Strength, N/mm ²	≥ 0,1
Initial Setting Time, min	> 20
Reaction to Fire	A1

Packaging and Storage

- Supplied on pallets in 30 kg PP bags.
- Store unopened in the original packaging in a dry, frost-free environment, stacked no more than 8 bags high. It is recommended to use within 6 months from the production date and within 1 week after opening the bag.

Document No: TDS.ENG.01.04

Revision No: 1

Validity Date: 10.08.2026

Liability: Above stated data obtained in lab conditions. Entegre will not be liable for any defect in product occurring by reason of events or conditions not within its control such as misuse, mishandling, improper storage or improper installation. Entegre reserves the right to revise the information contained herein without prior notice.

ENTEGRE

"Building Life"

SATENPER®Satin Finishing Plaster
Ready-to-Paint Surface

GYPSUM PLASTERS

Warnings

- No foreign material (lime, cement, gypsum, etc.) should be added to the prepared mortar.
- Application is recommended at temperatures between +5 °C and +35 °C.
- Depending on the ambient temperature, SATENPER® must be allowed to cure for at least 3 days before subsequent applications are carried out over it.
- Do not use outside the specified areas of application or contrary to the instructions for use.
- Do not inhale directly. In case of contact with eyes, rinse with plenty of water and seek medical advice if necessary.
- For further information, request the product Safety Data Sheet.
- Please consult us regarding all other application conditions and for technical questions.

Certificate of Conformity



TS EN 13279-1 / February 2009 / C6-20-2.0

Public Works Item No.: 10.240.5508

Document No: TDS.ENG.01.04

Revision No: 1

Validity Date: 10.08.2026

Liability: Above stated data obtained in lab conditions. Entegre will not be liable for any defect in product occurring by reason of events or conditions not within its control such as misuse, mishandling, improper storage or improper installation. Entegre reserves the right to revise the information contained herein without prior notice.



Hüseyinli Mah. Beykoz Cad.
No: 222/4 Çekmeköy - İstanbul

+90 (0216) 434 50 96

export@entegreharc.com.tr