



Areas of Use

GIPSFIX is a gypsum-based joint filler suitable for interior applications and used for filling gypsum board joints.

Advantages

- Suitable for interior applications.
- Provides easy, convenient and fast application.
- Thanks to the special additives in its formulation, it provides high adhesion and strength.
- Provides additional resistance to cracking.
- Provides a smooth and even surface.

Application

Surface Preparation

The application surface must be free of formwork oil, dust, paint and similar substances. The application surface must be dry and protected against moisture.

Mortar Preparation and Application

First, water is poured into a clean mixing container, then GIPSFIX is added (approximately 15-16 L of water for a 25 kg bag) and mixed until all lumps are completely eliminated. Allow the mixture to stand for 5 minutes, then mix again to obtain a homogeneous consistency.

The prepared GIPSFIX is applied to gypsum board joints so as to embed the joint tape, followed by a second coat to completely fill the tapered edges of the boards. If necessary, additional coats may be applied after allowing each coat to fully set.

Consumption

Approx. 1 kg/m² (for 2 mm application thickness).

Technical Values

Compressive Strength, N/mm ²	≥ 3,0
Flexural Strength, N/mm ²	≥ 2,0
Adhesion Strength, N/mm ²	≥ 0,4
Initial Setting Time, min	60-80

ENTEGRE

"Building Life"

GIPSFIX®

Gypsum-Based Joint Filler



GYPSUM PLASTERS

Packaging and Storage

Gypsum-based products should be stored in a closed and dry environment. Gypsum bags should be stacked on pallets so that they do not come into contact with damp floors or walls. Long-term outdoor storage is not recommended.

All gypsum-based plasters are sensitive to fluctuating humidity conditions and the effects of ageing over time. This may cause variations in setting time and adversely affect product performance.

When stored under the recommended storage conditions, the products have a shelf life of 6 months from the date of production.

- Please consult us regarding all other application conditions and for technical questions.

Certificate of Conformity

TS EN 13963 - Complies with Type 3B.

Warnings

- No foreign material (lime, cement, gypsum, etc.) should be added to the prepared mortar.
- Application is recommended at temperatures between +5 °C and +35 °C.
- Do not use outside the specified areas of application or contrary to the instructions for use.
- Do not inhale directly. In case of contact with eyes, rinse with plenty of water and seek medical advice if necessary.
- For further information, request the product Safety Data Sheet.

Document No: TDS.ENG.01.07

Revision No: 1

Validity Date: 10.08.2026

Liability: Above stated data obtained in lab conditions. Entegre will not be liable for any defect in product occurring by reason of events or conditions not within its control such as misuse, mishandling, improper storage or improper installation. Entegre reserves the right to revise the information contained herein without prior notice.

ENTEGRE

Hüseyinli Mah. Beykoz Cad.
No: 222/4 Çekmeköy - İstanbul

+90 (0216) 434 50 96

export@entegreharc.com.tr

Page 2