

ENTEGRE

"Building Life"

ROOF RIDGE ADHESIVE MORTAR

Cement-Based Polymer-Modified
Roof Ridge Tile Bedding Mortar



TECHNICAL MORTARS

Areas of Use

Used for bonding and securing roof ridge tiles.

Advantages

- Provides high adhesion.
- Complements the visual appearance of the roof thanks to its colour, which is close to that of roof tiles.
- Easy to prepare and apply.

Application

Surface Preparation

The application surface must be thoroughly cleaned of form oil, dust, paint and any substances that may reduce adhesion.

The application surface must be dampened with water.

Mortar Preparation and Application

ROOF RIDGE ADHESIVE MORTAR is mixed using a trowel or an electric mixer (6-6,5 L water / 25 kg bag).

During mortar preparation:

- First pour the water into the container, then add ROOF RIDGE ADHESIVE MORTAR. Mix thoroughly until no lumps remain.
- Allow to rest for 5 minutes, then remix until a homogeneous mixture is obtained.

- When positioning the ridge tiles along the roof ridge, bond them together at their interlocking sections using ROOF RIDGE ADHESIVE MORTAR.
- Fill the sides of the ridge tiles completely with ROOF RIDGE ADHESIVE MORTAR, leaving no gaps.
- After 1 hour, give the mortar its final shape using a damp sponge.

Consumption

Approximately 600 g per ridge tile.

Technical Values

Colour	Roof tile
Density, kg/m ³	1400 ± 200
Workability Time, min	≥ 100
Adjustment Time, min	≥ 3
Compressive Strength, N/mm ²	≥ 5.0 (M 5)
Maximum Particle Size, mm	≤ 2
Water Absorption, kg/m ² .min ^{0,5}	≤ 2,5
Water Vapour Permeability Coefficient (μ)	5/20
Reaction to Fire	A1

Document No: TDS.ENG.03.03

Revision No: 1

Document Revision Date: 07.08.2026

Liability: Above stated data obtained in lab conditions. Entegre will not be liable for any defect in product occurring by reason of events or conditions not within its control such as misuse, mishandling, improper storage or improper installation. Entegre reserves the right to revise the information contained herein without prior notice.



Hüseyinli Mah. Beykoz Cad.
No: 222/4 Çekmeköy - İstanbul

+90 (0216) 434 50 96

export@entegreharc.com.tr

ENTEGRE

"Building Life"

ROOF RIDGE ADHESIVE MORTAR

Cement-Based Polymer-Modified
Roof Ridge Tile Bedding Mortar



TECHNICAL MORTARS

Packaging and Storage

- Supplied on pallets in 25 kg kraft bags.
- When stored unopened in its original packaging in a dry, frost-free environment, stacked no more than 8 bags high and without direct contact with the ground, the shelf life is 1 year from the date of manufacture. Once opened, the bag should be consumed within 1 week.

Warnings

- Do not add any foreign material (lime, cement, gypsum, etc.) to the prepared mortar.
- Application is recommended at temperatures between +5 °C and +35 °C.
- Do not apply to frozen surfaces or surfaces exposed to sunlight for extended periods.
- Mortar that has exceeded its working time must not be reused under any circumstances.
- Do not use outside the specified areas of application or contrary to the application instructions.
- Do not inhale directly. In case of contact with eyes, rinse thoroughly with plenty of water and seek medical advice if necessary.

- Request the product Safety Data Sheet for further information.
- Please consult us regarding all other application conditions and technical questions.

Certificate of Conformity



TS EN 998-2 / January 2017

Type T (Thin-Layer Masonry Mortar)

Document No: TDS.ENG.03.03

Revision No: 1

Document Revision Date: 07.08.2026

Liability: Above stated data obtained in lab conditions. Entegre will not be liable for any defect in product occurring by reason of events or conditions not within its control such as misuse, mishandling, improper storage or improper installation. Entegre reserves the right to revise the information contained herein without prior notice.



Hüseyinli Mah. Beykoz Cad. No: 222/4 Çekmeköy - İstanbul
+90 (0216) 434 50 96
export@entegreharc.com.tr

Page 2