



Areas of Use

Used as a fine finishing plaster over conventional and cement-based plaster applications in interior and exterior areas.

Properties

- Provides a smooth surface for final coat applications.
- Provides a cost advantage.
- Allows easy and fast application.

Application

Surface Preparation

The surface must be free from formwork oil, dust, paint and substances that may reduce adhesion.

Cracks and holes must be repaired with suitable Entegre Repair Mortars before application.

The application surface should be dampened with water if necessary.

Mortar Preparation and Application

FİNTEK® is prepared by mixing manually or with a hand mixer (4,5-5,5 L water/25 kg bag).

Apply with a plastering trowel in a single coat at a thickness of 3-10 mm.

After this process, once the plaster has hardened sufficiently, float the plaster surface and finish with a damp sponge.

Consumption

Approx. 1,7 kg/m² for 1 mm thickness.

Technical Values

Dry Bulk Density, kg/m ³	1600 ± 300
Compressive Strength, N/mm ²	≥ 6,0 (CS IV)
Bond Strength, N/mm ²	≥ 0,2 (FP:B)
Capillary Water Absorption, kg/m ² .min ^{0.5}	W0
Water Vapour Permeability Coefficient, μ	≤ 25
Mean Thermal Conductivity, W/m.K (λ10,dry)	0,75
Reaction to Fire	A1



Packaging and Storage

- Supplied on pallets in 25 kg kraft bags.
- Store unopened in the original packaging in a dry, frost-free environment, stacked no more than 8 bags high and without direct contact with the floor. It is recommended to use within 1 year from the production date and within 1 week after opening the bag.
- Keep the packaging tightly closed when not in use.

Warnings

- No foreign material (lime, cement, gypsum, etc.) should be added to the prepared mortar.
- Application is recommended at temperatures between +5 °C and +35 °C.
- In windy conditions, FİNTEK® must be protected against rapid drying.
- To ensure product durability, the surface should be moistened with water at regular intervals for 3 days after application.
- For applications particularly during summer, a two-coat application is recommended where necessary to prevent the risk of cracking caused by rapid drying.

- The use of plaster mesh is recommended at junctions of different materials and at points where movement may occur.
- Depending on the ambient temperature, a minimum of 10 days should be allowed before applying subsequent coatings over FİNTEK®.
- Do not use outside the specified areas of application or contrary to the instructions for use.
- Do not inhale directly. In case of contact with eyes, rinse with plenty of water and seek medical advice if necessary.
- For further information, request the product Safety Data Sheet.
- Please consult us regarding all other application conditions and for technical questions.

Certificate of Conformity



TS EN 998-1 / February 2017 / A1-GP-CS IV